

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application:

LISTING OF CLAIMS:

Claim 1. (currently amended): A low specific gravity unsaturated polyester resin composition for lamp reflectors, characterized in that the composition comprises from 40 to 210 parts by weight of an inorganic filler having an average particle size of at least $0.5\text{ }\mu\text{m}$, ~~of and~~ from 30 to 160 parts by weight of a hollow filler having a pressure resistance of at least $2,100 \times 10^4\text{ N/m}^2$ based on 100 parts by weight of an unsaturated polyester resin and a crosslinking agent from 35 to 75 parts by weight of a crosslinking agent based on 100 parts by weight of the unsaturated polyester resin and the crosslinking agent, said crosslinking agent comprising:

(A) diallylphthalate monomer or diallylphthalate prepolymer, and

(B) a crosslinking agent selected from the group consisting of a styrene monomer, methyl methacrylate and triallylisocyanurate;

wherein the ratio by weight of the (A) to (B) lies in a range of 5:95 to 25:75, and

wherein the addition ratio by weight of the inorganic filler to the hollow filler lies within a range of 2:8 to 8:2.

Claim 2. (canceled).

Claim 3. (previously presented): A low specific gravity unsaturated polyester resin composition for lamp reflectors according to Claim 1, characterized in that said polyester resin is

obtained by polycondensing a total of 100 moles consisting of 20 to 50 moles of propylene glycol, 25 to 65 moles of neopentyl glycol and 15 to 25 moles of bisphenol A or hydrogenated bisphenol A based on 100 moles of at least one unsaturated polybasic acid selected from a group formed from fumaric acid and maleic anhydride.

Claim 4. (previously presented): A low specific gravity unsaturated polyester resin composition for lamp reflectors according to Claim 1, characterized in that the inorganic filler has an average particle size of 15 μ m or less.

Claim 5. (previously presented): A low specific gravity unsaturated polyester resin composition for lamp reflectors according to Claim 1, characterized in that the hollow filler has a true specific gravity of 0.3 to 0.7.

Claim 6. (previously presented): A low specific gravity unsaturated polyester resin composition for lamp reflectors according to Claim 1, characterized in that molded articles of the resin composition have a molding shrinkage ratio of -0.15 to +0.05%, a coefficient of linear expansion of $1.0 \times 10^{-5}/K$ to $2.5 \times 10^{-5}/K$, Barcol hardness of 5 to 25 when heated at 180°C and a specific gravity of 1.00 to 1.60.

Claim 7. (previously presented): A low specific gravity unsaturated polyester resin composition for lamp reflectors according to Claim 1, characterized in that the molded articles of the resin composition have a leveling of 5 to 20.

Claim 8. (previously presented): A molded article obtained by molding the low specific gravity unsaturated polyester resin composition for lamp reflectors according to Claim 1.

Claim 9. (original): A molded article according to Claim 8, characterized in that the molded article has a molding shrinkage ratio of -0.15 to +0.05%, a coefficient of linear expansion of $1.0 \times 10^{-5}/K$ to $2.5 \times 10^{-5}/K$, Barcol hardness of 5 to 25 when heated at 180°C and a specific gravity of 1.00 to 1.60.